

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency	Permeability	Temperature	Gravity	Loss	初透磁率比溫度係數
	使用頻率	初透磁率	居里溫度	比重	Factor 比損耗因子	
Material 材質	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ (x10-6MHZ)	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
C5C	0.01~0.5	1000	>130	4.8	<100 0.5	2~8

