

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency 使用頻率	Permeability 初透磁率	Temperature 居里溫度	Gravity 比重	Loss Factor 比損耗因子	初透磁率比 溫度系數
Material 材質	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu i$ (x10-6MHZ)	$\alpha \mu r$ (x10-6°C 20°C~70°C)
C6	0.01~0.5	1300	>100	4.7	<75 0.5	0~3

