

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency 使用頻率	Permeability 初透磁率	Temperature 居里溫度	Gravity 比重	Loss Factor 比損耗因子	初透磁率比 溫度系數
Material 材質	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ ($\times 10^{-6}$ MHZ)	$\alpha \mu_r$ ($\times 10^{-6}/^{\circ}\text{C}$ 20°C~70°C)
E1D	0.3~15	90	>300	4.8	<850 15	4~8

