

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative
特性	Frequency	Permeability	Temperature	Gravity	Loss	Temperature
	使用頻率	初透磁率	居里溫度	比重	Factor	初透磁率比溫度係數
					比損耗因子	
Material	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ (x10-6MHZ)	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
材質						
E3	0.4~20	80	>300	4.4	<160 20	55~130

