

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency	Permeability	Temperature	Gravity	Loss	初透磁率比溫度系數
	使用頻率	初透磁率	居里溫度	比重	Factor 比損耗因 子	
Material 材質	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ (x10-6MHZ)	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
F3B	0.1~2.0	280	>150	4.9	<65 2.0	10~30

