

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative
特性	Frequency	Permeability	Temperature	Gravity	Loss	Temperature
	使用頻率	初透磁率	居里溫度	比重	Factor	初透磁率比
Material					比損耗因	溫度係數
材質	ft(MHZ)	$\mu_{i ac}$	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ (x10-6MHZ)	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
F4D	0.1~1.0	500	>250	4.7	<50 0.5	10~20

