

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative
特性	Frequency	Permeability	Temperature	Gravity	Loss	Temperature
	使用頻率	初透磁率	居里溫度	比重	Factor 比損耗因子	coefficient 初透磁率比溫度系數
Material 材質	ft(MHZ)	μ_{iac}	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_i$ (x10-6MHZ)	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
Y11	3.0~80	40	>350	4.5	<400 60	50~70

