

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative
特性	Frequency	Permeability	Temperature	Gravity	Loss	Temperature
	使用頻率	初透磁率	居里溫度	比重	Factor	初透磁率比
Material	ft(MHZ)	$\mu_{i ac}$	T.C(°C)	d(g/cm3)	$\tan \delta / \mu_{i ac}$ (x10-6MHZ)	溫度係數
材質						
Y5E	20~120	20	>250	4.9	<500 100	2~10

