

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency	Permeability	Temperature	Gravity	Loss	初透磁率比溫度係數
Material	ft(MHZ)	$\mu_{i ac}$	T.C(°C)	d(g/cm3)	Factor	$\alpha \mu_r$
材質					比損耗因子	(x10-6/°C)
Y8B	0.5~20	60	>300	4.5	<400 20	5~15

