

Characteristics	Practical	Initial	Curie	Specific	Relative	Relative Temperature coefficient
特性	Frequency	Permeability	Temperature	Gravity	Loss	初透磁率比溫度係數
Material	ft(MHZ)	$\mu_{i ac}$	T.C(°C)	d(g/cm3)	Factor 比損耗因子	$\alpha \mu_r$ (x10-6/°C 20°C~70°C)
材質						
Y8L	0.5-15	80	>300	4.8	<1100 15	3~9

