

| Characteristics | Practical | Initial      | Curie       | Specific | Relative              | Relative       |
|-----------------|-----------|--------------|-------------|----------|-----------------------|----------------|
| 特性              | Frequency | Permeability | Temperature | Gravity  | Loss                  | Temperature    |
|                 | 使用頻率      | 初透磁率         | 居里溫度        | 比重       | Factor                | 初透磁率比          |
|                 |           |              |             |          | 比損耗因                  | 溫度係數           |
| Material        |           |              |             |          | $\tan \delta / \mu_i$ |                |
| 材質              | ft(MHZ)   | $\mu_{iac}$  | T.C(°C)     | d(g/cm3) | (x10-6MHZ)            | $\alpha \mu_r$ |
|                 |           |              |             |          |                       | (x10-6/°C      |
|                 |           |              |             |          |                       | 20°C~70°C)     |
| Y9              | 0.5~30    | 65           | >300        | 4.8      | <280 30               | 25~65          |

